

Amendments to the Claims:

The listing of claims will replace all prior versions, and listings of claims in the application:

Listing of Claims:

Claim 1. (original) Heat-sensitive composition which forms an image without the removal of material, which does not require any developing treatment after the stage of exposure to heat and comprises:

- a) a switchable polymer, and
 - b) an IR absorber,
- characterised in that it also comprises:
- c) a triazine compound, and
 - d) a novolak resin.

Claim 2. (currently amended) Heat-sensitive composition which forms an image without the removal of material, which does not require any developing treatment after the stage of exposure to heat and comprises:

- a) a switchable polymer,
- b) an IR absorber,
- c) a triazine compound, and
- d) a novolak resin; ~~Composition according to claim 1,~~ characterised in that the said switchable polymer has attached hydrophilic groups and becomes lipophilic through the effect of IR radiation.

Claim 3. (currently amended) Composition according to claim 2, characterised in that ~~the~~ said attached hydrophilic groups are carboxyl groups.

Claim 4. (original) Composition according to claim 1, characterised in that the said switchable polymer is obtained by the acid hydrolysis of a copolymer of methyl vinyl ether and maleic anhydride.

Claim 5. (currently amended) Composition according to claim 1, characterised in that the quantity of the said switchable polymer is from 50% to 75% by weight.

Claim 6. (currently amended) Composition according to claim 5, characterised in that the quantity of the said switchable polymer is from 55% to 70% by weight.

Claim 7. (previously presented) Composition according to claim 1, characterised in that the IR absorber is a cyanine dye.

Claim 8. (currently amended) Heat-sensitive composition which forms an image without the removal of material, which does not require any developing treatment after the stage of exposure to heat and comprises:


a) a switchable polymer,

b) an IR absorber,

c) a triazine compound, and

d) a novolak resin; ~~Composition according to claim 1, characterised in that the~~

IR absorber has the following formula



Claim 9. (currently amended) Composition according to claim 1, characterised in that the quantity of the said IR absorber is from 1% to 12% by weight.

Claim 10. (currently amended) Composition according to claim 1, characterised in that the quantity of the said IR absorber is from 5% to 10% by weight.


Claim 11. (currently amended) Heat-sensitive composition which forms an image without the removal of material, which does not require any developing treatment after the stage of exposure to heat and comprises:

a) a switchable polymer,

b) an IR absorber,

c) a triazine compound, and

d) a novolak resin; ~~Composition according to claim 1,~~ characterised in that the triazine compound has the structural formula:



where at least one of the substituents R1, R2 and R3 is NR'R'' and the others are H or NR'R'' and at least one of the substituents R' and R'' is -CH₂-O-Alk₁₋₄C and the others R' and R'', which are the same or different from each other, are H or -CH₂-O-Alk₁₋₄C.

Claim 12. (original) Composition according to claim 11, characterised in that two of the substituents R1, R2 and R3 are NR'R''.

Claim 13. (original) Composition according to claim 11, characterised in that all three substituents R1, R2 and R3 are NR'R''.

Claim 14. (original) Composition according to claim 13, characterised in that the three R' substituents are H, two of the R'' substituents are -CH₂-O-CH₃ and the third R'' substituent is -CH₂-O-C₄H₉.

Claim 15. (original) Composition according to claim 13, characterised in that the three R' substituents are $-\text{CH}_2\text{-O-CH}_3$ and the three R'' substituents are $-\text{CH}_2\text{-O-CH}_3$.

Claim 16. (original) Composition according to claim 13, characterised in that the three R' substituents are $-\text{CH}_2\text{-O-CH}_3$ and the three R'' substituents are $-\text{CH}_2\text{-O-C}_4\text{H}_9$.

Claim 17. (original) Composition according to claim 12, characterised in that the two R' substituents are $-\text{CH}_2\text{-O-CH}_3$ and the two R'' substituents are $-\text{CH}_2\text{-O-C}_4\text{H}_9$.

Claim 18. (currently amended) Composition according to claim 1, characterised in that the quantity of ~~the~~ said triazine compound is from 10 to 30% by weight.

Claim 19. (currently amended) Composition according to claim 1, characterised in that the quantity of ~~the~~ said triazine compound is from 15 to 25% by weight.

Claim 20. (currently amended) Composition according to claim 1, characterised in that ~~the~~ said novolak resin has a weight average molecular weight of between 2,000 and 14,000.

Claim 21. (currently amended) Composition according to claim 1, characterised in that ~~the~~ said composition comprises at least two novolak resins, a first having a weight average molecular weight of between 3,000 and 5,000 and a second having a weight average molecular weight of between 6,000 and 11,000.

Claim 22. (previously presented) Composition according to claim 1, characterised in that the total quantity of novolak resin is from 1 to 20% by weight.

Claim 23. (previously presented) Composition according to claim 1, characterised in that the total quantity of novolak resin is from 5 to 20% by weight.

Claim 24. (previously presented) Negative lithographic plate comprising a substrate coated with a composition according to claim 1.

Claim 25. (currently amended) Method for obtaining a negative image on a substrate coated with a composition which is first hydrophilic and then lipophilic after exposure to heat, without the removal of material, ~~the~~ said method being characterised in that ~~the~~ said negative image is obtained by applying an energy equal to or lower than 250 mJoule/cm² ~~a small quantity of energy to the~~ said composition.

Claim 26. (currently amended) Method according to claim 25, characterised in that ~~the~~ said composition is a heat-sensitive composition which forms an image without the removal of material, which does not require any developing treatment after the stage of exposure to heat and comprises: a) a switchable polymer, and b) an IR absorber, characterised in that it also comprises: c) a triazine compound, and d) a novolak resin.

Claim 27. (new) An imaged lithographic plate comprising a substrate coated with a composition according to claim 1, said coated composition being image-wise exposed to an energy equal to or lower than 250 mJoule/cm² without any subsequent developing treatment.